



Osstyrol L-ABS IQ/L-TPU

Description

Sheets or foils, produced from conductive, recycled ABS with a percentage of TPU with a coextruded, conductive TPU-layer.

Product information	Test method	Unit	L-TPU	L-ABS IQ
Mechanical properties				
Yield stress ⁽¹⁾	ISO 527	MPa	19	1300
Tensile strain at yield ⁽¹⁾	ISO 527	%	24	
Elongation at break ⁽¹⁾	ISO 527	%	730	
Tensile modulus	ISO 527	MPa	250	
Flexural strength	ISO 178	MPa		
Charpy impact strength 23°C / -30°C ⁽²⁾	ISO 179/2C	kJ/m ²	NB	
Charpy notched impact strength 23°C / -30°C ⁽²⁾	ISO 179/2C	kJ/m ²	NB	
Izod notched impact strength 23°C	ISO 180/1A	kJ/m ²		
Shora A hardness	DIN 53505	Shore A ca.-value	85	
Thermal properties				
Vicat softening point VST/B/50	ISO 306	°C		
Vicat point VST/A/120	ISO 306	°C		
Deflection temperature 1.8 Mpa (HDT A)	ISO 75-2	°C		
Deflection temperature 0.45 Mpa (HDT B)	ISO 75-2	°C		
Electrical properties				
Realtive permittivity at 100Hz / 1MHz	IEC 60250			
Dissipation factor at 100 Hz / 1MHz	IEC 60250	Ohm cm		
Surface resistivity, top-side	DIN 61340	Ohm	≤ 10E6	≤ 10E6
Volume resistivity	DIN 61340	Ohm cm	≤ 10E6	≤ 10E6
Electric strength K20/P50	IEC 60243-1	kV/mm		
Optical properties				
Surface gloss	DIN 67530	%		
Flammability				
Flammability UL-Standard at thickness d=1.6 mm	UL 94	Class		
Testing of electrical insulating material, Method FH	IEC 60707	Level		
Testing of electrical insulating material, Method BH	IEC 60707	Level		
Testing of car industry's materials (d>1mm)	FMVSS 302			
Other properties				
Density at 23 °C	ISO 1183	g/cm ³	1,23	
Abrasion	DIN 53516	mm ² ca.-value		

Particularities

Important: The given values apply to the product condition upon delivery at customer. In particular, the conductivity is affected by storing conditions and storing duration as well as the kind of further processing. Depending on individual parameters (elongation ratio, residual wall thickness, temperatures) deep drawig influences the conductivity to different extents and under extreme conditions, may lead to decomposition of conductivity. Measurement of conductivity is according to DIN 61.340-2-3.

We recommend to thermoform the material within 3 months after production because the material is hygroscopic. .

⁽¹⁾ Sample: 400 µm thickness

⁽²⁾ Sample: 4,00 mm thickness

NB: no break

Note

The information submitted in this publication is based on our current knowledge and experience. Tested are uncoloured products. In view of many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of the suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.